

**P 730**  
**CALCINED ALUMINA**

<b>Chemical analysis:</b>		<b>%</b>
	<b>SiO<sub>2</sub></b>	<b>0.01</b>
	<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>99.00</b>
	<b>Na<sub>2</sub>O</b>	<b>0.40</b>
	<b>K<sub>2</sub>O</b>	-
	<b>CaO</b>	-
	<b>MgO</b>	-
	<b>TiO<sub>2</sub></b>	-
	<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>0.02</b>
	<b>ZrO<sub>2</sub></b>	-
	<b>L.O.I.</b>	<b>0.5</b>
	<b>B.e.t. (m<sup>2</sup>/gr)</b>	<b>13</b>
<b>Particle size distribution:</b>	<b>D<sub>10</sub> (µm)</b>	<b>0.8</b>
	<b>D<sub>50</sub> (µm)</b>	<b>5</b>
	<b>D<sub>90</sub> (µm)</b>	<b>21</b>