

M 21-03

CLAY

Chemical analysis (fired): %

SiO₂	74.90
Al₂O₃	20.30
Na₂O	0.20
CaO	0.20
MgO	0.30
TiO₂	1.90
Fe₂O₃	0.50
K₂O	1.70
L.O.I.	5.30

Water absorption% (1200°C): **3.50**

Firing shrinkage % (1200°C): **4.60**

Granulometry: **0-3 cm**