

W 8/W
SODIUM BENTONITE

Chemical analysis:		%
	SiO₂	71.50
	Al₂O₃	14.50
	Na₂O	2.20
	K₂O	2.00
	CaO	1.20
	MgO	4.00
	TiO₂	0.15
	Fe₂O₃	1.40
	L.O.I.	max 12
Sieve analysis:	> 180 μm	5.5
Swelling index:	30 – 35 ml/2g	