

AR 42
KAOLINITIC-ILLITE CLAY

Chemical analysis:	%
SiO₂	59.40
Al₂O₃	27.00
Na₂O	0.20
K₂O	2.60
CaO	0.20
MgO	0.30
TiO₂	1.60
Fe₂O₃	1.00
ZrO₂	-
L.O.I.	7.50

Granulometry: 0 – 3 cm